



# LOCTITE<sup>®</sup> 7088<sup>™</sup>

December 2008

## PRODUCT DESCRIPTION

LOCTITE<sup>®</sup> 7088<sup>™</sup> provides the following product characteristics:

<b>Technology</b>	Primer for LOCTITE <sup>®</sup> anaerobic adhesives and sealants
<b>Chemical Type</b>	Dimethacrylate ester
<b>Appearance</b>	Turquoise Paste <sup>LMS</sup>
<b>Appearance (form)</b>	Stick
<b>Cure</b>	Anaerobic
<b>Application</b>	Cure acceleration of LOCTITE <sup>®</sup> anaerobic products

LOCTITE<sup>®</sup> 7088<sup>™</sup> is a reactive monomer based "solvent free" surface primer that is supplied as a wax-like semi-solid, conveniently packaged in a self-feeding stick applicator. LOCTITE<sup>®</sup> 7088<sup>™</sup> was designed to promote the cure speed of Loctite<sup>®</sup> anaerobic products. It is especially recommended for applications with passive metals or inert surfaces and with large bond gaps.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.03
Penetration, ISO 2137, unworked, 1/10mm	100 to 200 <sup>LMS</sup>

Flash Point - See MSDS

## TYPICAL PERFORMANCE OF CURED MATERIAL

Cured for 1 hour @ 22 °C, using LOCTITE<sup>®</sup> 248<sup>™</sup>

Breakaway Torque, ISO 10964:

3/8 x 16 steel nuts and bolts (degreased)	N·m (lb.in.)	≥8.0 <sup>LMS</sup> (≥70)
---	-----------------	------------------------------

## GENERAL INFORMATION

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected with a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).**

**Under no circumstances should activator and adhesive be mixed directly as liquids. Use only in a well ventilated area.**

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some cases these aqueous washes can affect the cure and performance of the adhesive.

## Directions for use:

1. For best results, clean all surfaces (external and internal) with a LOCTITE<sup>®</sup> cleaning solvent and allow to dry.
2. Advance only enough product to use at the time of application. Do not retract excess product.
3. Remove any skin that may have formed on the top of the stick.
4. Apply sufficient product to fill the threads on one side of the bolt where the nut will be engaged.
5. Recap product after use.
6. Apply LOCTITE<sup>®</sup> anaerobic product to the opposite side of the bolt.
7. Assemble and tighten as required. Threading the nut will mix anaerobic and primer in the threads.

## Loctite Material Specification<sup>LMS</sup>

LMS dated February 28, 2008. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

## Storage

Store product in the unopened container in a dry location. Material removed from containers may be contaminated during use. Do not return liquid to original container. Storage information may be indicated on the product container labeling. **Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.** Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those recommended. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

## Conversions

(°C x 1.8) + 32 = °F  
 kV/mm x 25.4 = V/mil  
 mm / 25.4 = inches  
 μm / 25.4 = mil  
 N x 0.225 = lb  
 N/mm x 5.71 = lb/in  
 N/mm<sup>2</sup> x 145 = psi  
 MPa x 145 = psi  
 N·m x 8.851 = lb·in  
 N·m x 0.738 = lb·ft  
 N·mm x 0.142 = oz·in  
 mPa·s = cP

**Note**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.2